

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
14 November 2002 (14.11.2002)

PCT

(10) International Publication Number
WO 02/090448 A2

(51) International Patent Classification: C09C

(21) International Application Number: PCT/EP02/04020

(22) International Filing Date: 11 April 2002 (11.04.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
01111320.6 9 May 2001 (09.05.2001) EP(71) Applicant (for all designated States except US): MERCK
PATENT GMBH [DE/DE]; Frankfurterstrasse 250, 64293
Darmstadt (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): ANSELMANN,
Ralf [DE/DE]; Muhlstrasse 11, 67305 Ramsen (DE).
AMBROSIUS, Klaus [DE/DE]; Am Schloss Stockau
13, 64807 Dieburg (DE). MATHIAS, Marcus [DE/DE];
Bleichstrasse 4a, 64579 Griesheim (DE).(74) Common Representative: MERCK PATENT GMBH;
Frankfurterstrasse 250, 64293 Darmstadt (DE).(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VN, YU, ZA, ZM, ZW.(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR,
GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR,
NE, SN, TD, TG).

Published:

— without international search report and to be republished
upon receipt of that reportFor two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: EFFECT PIGMENTS BASED ON COATED GLASS FLAKES

(57) Abstract: The present invention relates to effect pigments based on thin glass flakes and to a method for the production of such pigments. The resulting pigment can be used in any application for which pearlescent pigments have been heretofore used such as, for example, in plastics, paints, inks, cosmetic formulations, coatings including solvent or waterborne automotive paint systems, powder coatings, inks and agriculture foils.

WO 02/090448 A2

Rec'd - CIPRO 10 NOV 2003
-1-

10/473710

Effect Pigments based on coated glass flakes

The present invention relates to effect pigments based on thin glass flakes, to a method for the production of such pigments and their use in plastics, paints, coatings, powder coatings, inks, printing inks, glasses, ceramic products, agriculture foils, and in cosmetic formulations.

Since more than 40 years iridescent luster effects can be achieved using so called nacreous or pearlescent pigments. Various alternative techniques have been developed to create colour/lustre effects. The most important, economic and common way to make these pigments is to coat a platelet shaped carrier with high refractive substances like TiO_2 , Fe_2O_3 , SnO_2 , ZrO_2 , Cr_2O_3 or combinations of these or with alternating layers of high and/or low refractivity. So far the nearly exclusively used carrier is wet ground muscovite mica. It is cheap, readily available and easy to cleave into smooth and very thin platelets. These can be classified into any desired particle size distribution. Additionally, pigments based on mica are very stable towards chemical, mechanical or thermal treatment. But there are some disadvantages of mica, since it is a natural product and shows inconsistencies from source to source and even from batch to batch. This has to be overcome by adjusting the processing parameters. Natural mica contains impurities like quartz which makes the processing more complicated (abrasion of grinding tools, waste) or like Fe, Mn, Cu which makes the masstone yellowish grey rather than white. When ground it yields platelets showing a broad distribution of thicknesses and diameters. This can be reduced by proper classification but will never lead to uniform shape.

In the past researchers tried to find corresponding alternatives to mica which keep the advantages of it but did not contain the above mentioned disadvantages.

- 2 -

A wide variety of other platy materials have been proposed as substitute for mica in the patent literature. These include non-soluble inorganic materials such as glass, enamel, china clay, porcelain, natural stones or other siliceous substances, metal objects and surfaces of organic polymer materials such as polycarbonate as disclosed for example in U.S. Patents 3,123,485, 3,219,734, 3,616,100, 3,444,987, 4,552,593 and 4,735,869. While glass has been mentioned as a possibility on many occasions, for instance in U.S. Patent 3,331,699, commercial pearlescent products are not made using glass and experience has shown that products made using glass as the platelet substrate have rather poor quality.

U.S. Patent 3,331,699 discloses that glass flakes may be coated with a translucent layer of particles of a metal oxide having a high index of refraction, such as titanium dioxide, provided there is first deposited on the glass flakes a nucleating substance which is insoluble in the acidic solution from which the translucent layer of metal oxide is deposited. The patent does not mention the necessity of a smooth transparent film, not particles, being necessary for quality interference pigments to be developed. The patent teaches that the nature of the glass is not critical, but that the presence of the nucleated surface is critical. It is further stated that there are only a small number of metal oxide compounds which are insoluble in the acidic solution and capable of forming a nucleated surface on the glass flakes; tin oxide and a fibrous boehmite form of alumina monohydrate are the only two such materials disclosed. As demonstrated in the examples below, products prepared according to the teachings of this patent are poor in quality.

U.S. Patent 5,436,077 teaches a glass flake substrate which has a metal covering layer on which is formed a dense protective covering layer of a metal oxide such as titanium dioxide. In this patent, the nature of the glass is unimportant, the metallic coating provides the desired appearance and the overcoating of the metal oxide is present to protect the metallic layer from corrosive environments.

- 3 -

EP 0 912 640 B1 teaches the coating of thick flakes of C glass having a first coating comprising iron oxide or rutile titanium dioxide thereon. The disadvantage of C glass is the limited thermal stability. As disclosed in the EP 0 912 640 B1 the rutile pigments prepared according to the corresponding examples were calcined at temperatures not higher than 600 °C. It is well known that the calcining temperature is of essential importance for the stability of rutile pigments, especially for outdoor applications. To yield sufficiently stabilized rutile TiO₂ layers on a substrate calcining temperatures of at least 800 °C are requested.

For the preparation of pearlescent pigments the transparency and the thickness of the platy substrate are very important. For the first time EP 0 289 240 B1 discloses the manufacturing of extremely thin glass flakes at reasonable costs. According to the claimed process the glass flakes cannot be only made in any desired composition, e. g., from pure SiO₂, but also in any thickness tailored for the application wanted down to below 0.8 µm.

It is an object of the present invention to overcome the problems of the prior art and to provide novel effect pigments which have advantageous application properties. This object is achieved by the inventive effect pigments based on very thin glass flakes having the following characteristics:

- (1) thickness of the glass flakes $\leq 1.0 \mu\text{m}$
- (2) high temperature and mechanical stability
- (3) smooth surfaces

The present invention relates to effect pigments based on glass flakes with a thickness of $\leq 1.0 \mu\text{m}$ coated with one or more layers with a high and/or a low reflective index. The thickness of the glass flakes is preferably $\leq 0.8 \mu\text{m}$ and especially $\leq 0.5 \mu\text{m}$. Especially preferred are thin glass flakes with a softening point $\geq 800 \text{ }^\circ\text{C}$.

Glass can be classified for example as A glass, C glass, E glass, ECR glass.

- 4 -

For the present invention quartz glass is preferred but the production of this glass is very expensive. Glass types which fulfill the feature of the requested softening point are quartz glass, and any other glass composition having a softening point of ≥ 800 °C. Glass flakes which fulfill the requirements are special glasses like e. g. Schott Duran or Supremax types. The softening point in the present invention is defined, according to ASTM C 338 as the temperature at which a uniform fiber of glass with a diameter of 0.55-0.75 mm and a length of 23.5 cm increases its length by 1 mm/min when the upper 10 cm is heated at a rate of 5 °C/min.

Suitable glass flakes preferably prepared according to EP 0 289 240 B1 are characterized in that they contain an average particle size in the range of 5 - 1000 μm , preferably in the range of 5-150 μm . Preferred glass flakes have an average particle size in the range of 5-150 μm and a thickness of 0.1-0.5 μm , preferably of 0.1-0.3 μm . The aspect ratio of glass flakes is in the range of 10-300, preferably in the range of 50-200.

The glass particles can be coated with one or more layers selected from the group consisting of metal oxides, metal suboxides, metal fluorides, metal oxyhalides, metals chalcogenides, metal nitrides, metal sulfides, metal carbides, or mixtures thereof.

Examples of suitable metal oxides are TiO_2 , Fe_2O_3 , TiFe_2O_5 , Ti suboxides, Fe_3O_4 , Cr_2O_3 , Al_2O_3 , SiO_2 , ZrO_2 , ZnO , SnO_2 , CoO , Co_3O_4 , VO_2 , V_2O_3 , $\text{Sn}(\text{Sb})\text{O}_2$ or mixtures thereof. The TiO_2 layer can be in the rutile or anatase modification, preferably the TiO_2 layer is rutile. Especially preferred are glass flakes coated with TiO_2 and/or Fe_2O_3 .

Metal sulfide coatings on glass flakes are preferably selected from sulfides of tin, silver, lanthanum, rare earth metals, preferably cerium, chromium, molybdenum, tungsten, iron, cobalt and/or nickel.

The glass flakes can be coated in the same way as e. g. mica based pearl lustre pigments. Coatings with a metal oxide may be accomplished by any

- 5 -

known methods, such as hydrolysis of a metal salt by heating or alkali, which deposits hydrated metal oxide, optionally followed by calcination.

5 In general, the procedure involves the dispersing of the thin glass flake particles and combining that dispersion with a precursor which forms a hydrous metal oxide film coating on the flakes.

10 After the glass is dispersed in water and placed in an appropriate vessel, the appropriate metal salts are added. The pH of the resulting dispersion is maintained at an appropriate level during the addition of the metal salts by simultaneous feeding a suitable base, for example sodium hydroxide, to cause precipitation of the hydrous metal dioxide on the glass flakes. An aqueous acid, for example hydrochloric acid, can be used for adjusting the pH. The
15 coated platelets can, if desired, be washed and dried before being calcined to the final pigment. The procedure is described in detail in U.S. Patent 5,433,779 and in the German Patents 14 67 468, 19 59 998, 20 09 566, 22 14 545, 22 15 191, 22 44 298, 23 13 331, 25 22 572, 31 37 808, 31 37 809,
20 31 51 343, 31 51 354, 31 51 355, 32 11 602 and 32 53 017.

The effect pigments of the present invention are preferably prepared by wet-chemically coating of the glass flakes or by gas phase decomposition of
25 volatile metal compounds (CVD, PVD) or electroless plating.

The effect pigments obtained in this way are characterized in that one or more homogeneous layers enrobing the uniform thin glass flakes.

30 Preferred effect pigments of the present invention are given in the following:
glass flake + TiO_2 (rutile)
glass flake + Fe_2O_3
glass flake + Fe_3O_4
35 glass flake + TiFe_2O_5
glass flake + Cr_2O_3
glass flake + ZrO_2

- 6 -

glass flake + Sn(Sb)O_2 glass flake + BiOCl glass flake + Al_2O_3 glass flake + Ce_2S_3

5

glass flake + MoS_2

In general, the layer thickness ranges from 0.1 to 1000 nm, preferably from 0.2 to 300 nm. The optical layer thickness will in general be adapted to the particular application. Preferred pigments are coated with one or two layers.

10

To enhance the light and weather stability it is frequently advisable, depending on the field of application, to subject the coated glass flakes to a surface treatment. Useful surface treatments include for example the processes described in DE-C 22 15 191, DE-A 31 51 354, DE-A 32 35 017 or DE-A 33 34 598, DE 40 30 727 A1, EP 0 649 886 A2, WO 97/29059, WO 99/57204, U.S. 5,759,255. This surface treatment further enhances the chemical stability of the pigments and/or facilitates the handling of the pigment, especially its incorporation into various application media.

15

20

The effect pigments of the present invention are advantageous useful for many purposes, such as the coloring of plastics, glasses, ceramic products, agriculture foils, decorative cosmetic formulations and in particular coatings, especially automotive coatings, and inks, including printing inks. All customary printing processes can be employed, for example offset printing, intaglio printing, bronze printing, flexographic printing. Furthermore they can be used as functional pigments like conductive pigments, as magnetic pigments or to make media, for example plastics, board products and papers, laser-markable.

25

30

The effect pigments of the present invention are also advantageously useful for these applications in admixture with filler pigments or transparent and hiding white, colored and black organic and inorganic pigments and also with conventional transparent, colored and black luster pigments based on metal oxide coated mica, TiO_2 flakes, SiO_2 flakes or Al_2O_3 flakes and coated or

35

- 7 -

uncoated metal pigments, BiOCl pigments, platelet shaped iron oxides, or graphite flakes.

5 Additionally, the inventive pigment mixtures can contain organic or inorganic colourants, thixotropy agents, wetting agents, dispersing agents, water, organic solvent or solvent mixtures, etc.

10 The pigment mixtures of the invention are simple and easy to handle. The pigment mixtures can be incorporated into the system in which it is used by simple mixing. Laborious milling and dispersing procedures for the pigments are not necessary.

15 The coated glass flakes of the invention can be used for pigmenting and/or coating materials, printing inks, plastics, agricultural films, button pastes, for the coating of seed, for the colouring of food, coatings of foods, medicaments or cosmetic formulations. The concentration of the pigments in the system in which it is to be used for pigmenting is generally between 0.01 and 50 % by weight, preferably between 0.1 and 5 % by weight, based on the overall solids content of the system. This concentration is generally dependent on the specific application.

20 The coated glass flakes of the invention can be used for pigmenting and/or coating materials, printing inks, plastics, agricultural films, button pastes, for the coating of seed, for the colouring of food, coatings of foods, medicaments or cosmetic formulations. The concentration of the pigments in the system in which it is to be used for pigmenting is generally between 0.01 and 50 % by weight, preferably between 0.1 and 5 % by weight, based on the overall solids content of the system. This concentration is generally dependent on the specific application.

25 Plastics comprising the pigment mixture of the invention in amounts of 0.1 to 50 % by weight, in particular from 0.5 to 7 % by weight, are frequently notable for a particular brilliance.

30 In the coating sector, especially in automotive finishing, the glass flakes are employed in amounts of 0.5 to 10 % by weight.

35 In the pigmentation of binder systems, for example for paints and printing inks for intaglio, offset or screen printing, the pigment is incorporated into the printing ink in amounts of 2 - 50 % by weight, preferably 5 - 30 % by weight and in particular 8 - 15 % by weight.

- 8 -

The invention likewise provides pigment preparations comprising coated glass flakes, optionally effect pigments, binders and, if desired, additives, the said preparations being in the form of substantially solvent-free, free-flowing granules. Such granules contain up to 95 % by weight of the inventive pigments. A pigment preparation in which the glass flakes of the invention are pasted up with a binder and with water and/or an organic solvent, with or without additives, and the paste is subsequently dried and brought into a compact particulate form, e. g. granules, pellets, briquettes, a masterbatch or tablets, is particularly suitable as a precursor for printing inks.

The present invention therefore also provides formulations containing the pigments of the invention.

In order to further illustrate the invention, various non-limiting examples are set forth below. In these, as well as throughout the balance of this specification and claims, all parts and percentages are by weight and all temperatures are in degrees centigrade unless otherwise indicated.

Examples

Example 1 (Rutile Silver pigment) Prior Art

200 g flakes of E-glass (thickness: 5 μm ; diameter: 10-40 μm ; specific surface area: approximately 0.2 m^2/g) are suspended in 2 l of deionized water. With vigorous stirring the suspension is heated to 80 °C. After having adjusted the pH to 2.0 with dilute HCl a first layer of SnO_2 is precipitated onto the glass flakes by feeding a solution of 3 g $\text{SnCl}_4 \times 5 \text{H}_2\text{O}$ (in 10 ml conc. HCl plus 50 ml of DI water) into the suspension under simultaneous neutralization with 10 % NaOH over a period of about 1 h. To complete the reaction the suspension is kept stirring for another 15 min. The coating is continued by adjusting the pH to 1.8 with dilute HCl and then titrating 63.5 ml of TiCl_4 -solution (400 g TiCl_4/l DI water) against 10 % NaOH over a period of about 3 h. Having reached the desired layer thickness the coating is stopped,

- 9 -

stirred for another 15 min, filtered, washed with DI water and dried. After calcination at 800 °C for 30 min a silverwhite rutile pigment is yielded.

5 Example 2 (Rutile Silver pigment)

200 g flakes of E-glass (thickness: 0.5 µm; diameter: 10-40 µm; specific surface area: approximately 1.7 m²/g) are suspended in 2 l of DI water. The coating is carried out the same way as in example 1. Titration periods keep the same, only the amounts of solutions are adjusted to the different base material:

5 g SnCl₄ x 5 H₂O (in 15 ml conc. HCl plus 75 ml DI water)
196.3 ml of TiCl₄ solution (400 g TiCl₄/l DI water)

15 After calcination at 800 °C for 30 min a brilliant silverwhite rutile pigment is yielded.

20 Examples 3 and 4 (Rutile Interference Green pigment)

The coatings are started in the same ways as for examples 1 and 2, only the amount of TiO₂ (400 g TiCl₄/l DI water) coated was increased to yield green interference type pigments. The further steps are again carried out as described in examples 1 and 2.

To evaluate their properties draw down cards are made from all of these pigments. Additionally sprayed panels were prepared.

30 The pigments based on glass flakes with a thickness of 5.0 µm and 0.5 mm are checked for their coloristics and their visual performance.

35 Results:

- draw downcards and panels pigments with a thickness of 5.0 µm showed

- 10 -

very weak performance making a "dilute" impression. For the silver little brilliance and little hiding effect was observed while for the green a dull colour and little brilliance are found;

- a little better is the effect in the sunlight as some larger flakes show a kind of sparkle;
- completely different is the situation with a thickness of 0.5 mm pigments: They exceeded comparable mica pigments regarding brilliance, lustre and (for the green) chroma;
- particularly impressing is the high transparency combined with clear color;
- looking with the microscope shows that the surfaces of all pigments are well and uniformly coated and that the differences result mostly from the imperfect orientation of the 5 mm particles;

5

10

15

20

25

30

35

Claims

1. Effect pigments based on glass flakes with a thickness of $\leq 1.0 \mu\text{m}$ characterized in that the glass flakes are coated with one or more layers with a high and/or low refractive index.
2. Effect pigments according to claim 1, characterized in that the softening point of the glass flakes is $\geq 800^\circ\text{C}$.
3. Effect pigments according to claim 1 or 2, characterized in that the glass flakes are coated with one or more layers of metal oxides, metal suboxides, metal oxyhalides, metal fluorides, metal chalcogenides, metal nitrides, metal sulfides, metal carbides, or mixtures thereof.
4. Effect pigments according to claim 3, characterized in that the metal oxide is TiO_2 , Fe_2O_3 , TiFe_2O_5 , Ti suboxides, Fe_3O_4 , Cr_2O_3 , Al_2O_3 , SiO_2 , ZrO_2 , ZnO , SnO_2 , CoO , Co_3O_4 , VO_2 , V_2O_3 , Sn(Sb)O_2 or mixtures thereof.
5. Effect pigments according to claim 4, characterized in that the glass flakes are coated with TiO_2 , Fe_2O_3 or a mixture of TiO_2 and Fe_2O_3 .
6. Effect pigments according to claim 4 or claim 5, characterized in that the TiO_2 is in the rutile modification.
7. Effect pigments according to claim 3, characterized in that the coatings are metal sulfides selected from sulfides of tin, silver, lanthanum, rare earth metals, chromium, molybdenum, tungsten, iron, cobalt and/or nickel.
8. Effect pigments according to any of the claims 1 to 7, characterized in that the glass flakes are coated with one or two layers.
9. A method of preparing an effect pigment according to claim 1 which

- 12 -

comprises coating of the glass flakes by wet chemical coating, by chemical or physical vapor deposition or electroless plating and optionally calcining the coated glass flakes.

- 5 10. Use of the effect pigments according to claim 1 in plastics, coatings, powder coatings, paints, inks, printing inks, glasses, ceramic products, agriculture foils and in cosmetic formulations.
- 10 11. Use of the effect pigments according to claim 1 as conductive pigments, as magnetic pigments or as dopants for the laser-marking of papers and plastics.
- 15 12. Formulations containing the effect pigments according to claim 1.

20

25

30

35

PATENT COOPERATION TREATY

PCT

INTERNATIONAL PRELIMINARY EXAMINATION REPORT

(PCT Article 36 and Rule 70)

(Rationalised Report according to the Notice of the President of the EPO published in the OJ11/2001)

REC'D 07 MAR 2003

WIPO PCT


Applicant's or agent's file reference		FOR FURTHER ACTION		See Notification of Transmittal of International Preliminary Examination Report (Form PCT/IPEA/416)
101B085-sngs				
International application No.	International filing date (day/month/year)	Priority date (day/month/year)		
PCT/EP 02/ 04020	11/04/2002	09/05/2001		
International Patent Classification (IPC) or national classification and IPC				
C09C1/00				
Applicant				
MERCK PATENT GMBH et al.				

- This international preliminary examination report has been prepared by this International Preliminary Examining Authority and is transmitted to the applicant according to Article 36.
- This REPORT consists of a total of 2 sheets, including this cover sheet.
☐ This report is also accompanied by ANNEXES, i.e., sheets of the description, claims and/or drawings which have been amended and are the basis for this report and/or sheets containing rectifications made before this Authority (see Rule 70.16 and Section 607 of the Administrative Instructions under the PCT).

These annexes consists of a total of _____ sheets.

- This report contains indications relating to the following items:

- I ☒ Basis of the report
- II ☐ Priority
- III ☐ Non-establishment of opinion with regard to novelty, inventive step and industrial applicability
- IV ☐ Lack of unity of invention
- V ☒ Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement
- VI ☐ Certain documents cited
- VII ☐ Certain defects in the international application
- VIII ☐ Certain observations on the international application

Date of submission of the demand	Date of completion of this report
13/11/2002	27/02/2003
Name and mailing address of the IPEA/	Authorized officer
 European Patent Office D-80398 Munich Tel. (+49-89) 2399-0, Tlx: 523656 epnu d Fax: (+49-89) 2399-4465	MERGONI M. Tel. (+49-89) 2399 2828



**INTERNATIONAL PRELIMINARY
EXAMINATION REPORT**

International application No.PCT/ EP 02/ 04020

I. Basis of the report

The basis of this international preliminary examination is the application as originally filed.

V. Reasoned statement under Rule 66.2(a)(ii) with regard to novelty, inventive step or industrial applicability

In light of the documents cited in the international search report, it is considered that the invention as defined in at least some of the claims does not appear to meet the criteria mentioned in Article 33(1) PCT, i.e. does not appear to be novel and/or to involve an inventive step (see international search report, in particular the documents cited X and/or Y and corresponding claim references).